

Product Data Sheet

MCH 3713
High Density Polyethylene

Product Description

MCH3713 has been manufactured using Basell Lupotech G licensed technology.

General Information

Status : Commercial: Active

Application : MCH3713 is suitable for Film, Bags, Film extrusion (Blending partner, (Refuse) bags, T-shirt bags, carrier bags)

Notes: Typical values; not to be construed as specifications
Blown film: thickness 20 μm , extruded at melt temperature of 220°C, long stalk process, blow-up ratio 4:1

Processing: Recommended melt temperatures: 180 - 240°C
Recommended film thickness: 10 – 50 μm

Typical Properties	Typical Value	Unit	Test Method
Physical Properties			
Density (23 °C)	937	kg/cm ³	ISO 1183
MFI (190 °C /21.6Kg)	13	dg/min	ISO 1133
MFI (190 °C /2.16Kg)	0.1	dg/min	ISO 1133
Mechanical properties			
Tensile Modulus of elasticity	735	Mpa	ISO527-1,2
Max. Tensile Strength (MD)	46	Mpa	ISO 527-1;3
Max. Tensile Strength (TD)	46	Mpa	ISO 527-1;3
Tensile Strain at Break (MD)	550	%	ISO 527-1
Tensile Strain at Break (TD)	650	%	ISO 527-1
Elmendorf tear strength(MD)	210	mN	ISO 6383-2
Elmendorf tear strength(TD)	1100	mN	ISO 6383-2
Failure energy	7	J/mm	DIN 53373
Dart Drop Impact	120	g	ASTM D 1709
Thermal Properties			
Melting Point	127	°C	ISO 3146
Vicat Temp , (A50,50 °C /h , 10 N)	121	°C	ISO 306
Additives :Antioxidant -Heat stabilizer			

Packaging : Supplied in pellet form and can be packaged in 25Kg Bags, one ton semi bulk or 17 tons bulk containers.

Food packaging : The above mentioned grade meets the relevant requirements of plastics directive 2002/72/EC (06-08-2002) and its amendments till directive 2008/39EC relating to plastic materials and articles intended to come into contact with foodstuffs.

Pharmaceutical Application: The above mentioned grade meets the requirements of the European pharmacopeia version 6 section 3.1.5 for pharmaceutical application.

Conveying: Conveying equipment should be designed to prevent accumulation of fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

1. be equipped with adequate filters
2. is operated and maintained in such a manner to ensure no leaks develop
3. that adequate grounding exists at all times

We further recommended that good housekeeping will practiced throughout the facility

Storage : As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight and/or heat during storage. The storage location should also be dry, dust free and the ambient temperature should not exceed 50. It is also advisable to process polyethylene resins (in pelletized or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

Handling :Minimal protection to prevent possible mechanical injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapors.

Combustibility : Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources .in burning; polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

Note: this information is based on our current knowledge and experience .in view of many factors that may affect processing and application, this data does not relive processors from the responsibility of carrying out their own tests and experiments, neither does it imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.